

- •634 Route 228 P.O. Box 599 Mars, PA. 16046 724-625-3116 FAX 724-625-1640
- •4111 Walden Ave Lancaster, NY 14086 716-681-1581 FAX 716-681-1513
- •900 W. Smith Rd. Medina, OH 44256 330-723-7780 FAX 330-723-7780
- •7301 Bessemer Avenue Cleveland, OH 44127 216-341-2000 FAX 216-341-5833





ALUM-COATING™ Aluminum No Fiber Roof Coating - 1.2 Pound #23305

A quality aluminum reflective coating which is manufactured from a blend of select asphalts, solvents, resin and 1.2 pounds of aluminum paste per gallon. When the coating is applied, the aluminum flakes form even, overlapping layers on the surface. The layers protect the coating and the roof surface below from the sun, wind, rain, ice and snow.

Uses

 As a reflective coating which beautifies as it preserves and protects metal, composition, and asphalt built-up roofing.

Advantages

- Reduces indoor building temperatures in summer by reflecting the sun's rays. Saves energy.
- It is self-preserving. Its aluminum armor reflects most of the rays of the sun which oxidize and age the
 roof surface below.

Coverage

• Product yield will be approximately 0.33 to 0.5 gallons per 100 square feet on metal and 0.5 to 1 gallon on asphalt roofs. As a general rule, the smoother the surface, the less material is required.

Surface Preparation

• Remove all dirt, dust, debris and standing water by brooming or a pressure washer where necessary and where no danger or nuisance is caused to areas adjacent to work. Steel brush all rust or scale from metal roofs. Scrape back to a hard edge all loose or scaled coating. Make all necessary repairs to existing surface prior to coating. Split seams, blisters, and cracks in existing surface and flashings should be repaired with **WEATHERPROOF™** Roof Cement. Heavily weathered or exposed felt surfaces, as well as concrete, masonry, or weathered metal should receive an application of **WEATHERPROOF™** Asphalt Primer prior to coating. All surfaces must be dry prior to application.

Application

- Coating must be thoroughly stirred prior to and occasionally during use. Mechanical mixing, if practical, is recommended.
- Apply by spray with a standard mastic pump and gun sized by a knowledgeable pump dealer for the particular application or by pouring directly from the container and spreading with a soft roofing brush.

Application (continued)

Brush product out uniformly and evenly, taking care not to overwork it.

- Clean up with mineral spirits, but do not thin the product with this or any other solvent.
- If the product is difficult to spread in cooler temperatures, warm containers by storing them overnight in a room at 65° to 70° F.

Drying Time

• Four hours to touch at 70° F. & 50% relative humidity. Allow 7 to 14 days before exposure to foot traffic

Restrictions

- Minimum application temperature is 50° F. and rising.
- Do not apply to areas which pond water; do not use on dead level, tar base, or existing gravel roofs.
- Do not apply to new asphalt roofs which have cured <u>less</u> than 30 days, solvent based asphalt coatings <u>less</u> than 30-90 days old, or to asphalt emulsion coatings that have cured for less than 30 days.
- Do not use with PVC film.
- Do not use where material, once applied, may come into contact with potable water.
- Not for use on or with products containing coal tar.
- Do not use on slate shingles or apply directly to wood surfaces.
- Surfaces to be coated must be dry and clean and must remain so for 24 to 48 hours after application.
 Moisture will inhibit the leafing of the aluminum flakes, causing the product to dry brown or streaky or spotty.
- Not for use over rubber or plastic membranes asphalt modified only. For exterior use only.

Cautions

• This product is combustible. Keep away from heat, sparks, and open flame. Avoid breathing of vapors. Avoid repeated or prolonged contact with skin. If swallowed, do not induce vomiting. Contact Physician immediately. Keep container closed when not in use. KEEP AWAY FROM CHILDREN. Product label and Material Safety Data Sheet contain further information on the safe use of this product and precautions for the safe disposal of the container. They should be read and understood prior to use.

SPECIFICATIONS

Percent Solids by Weight	52%
Percent Solids by Volume	47%
Weight Per Gallon: Pounds	8.60
Flash Point - minimum	105° F. (Seta C.C.)
Viscosity at 77° F	500 cps.
Long-Term Service Temperature	60° F. to +160° F.
Water Resistance: Intermittent Exposure	
Water Resistance: Ponded	Poor
Solvent Resistance	Poor
U.V. Resistance	Excellent
Reflectivity: Average	67%
VOC	

PACKAGING INFORMATION

Product Number	<u>Size</u>	Quantity	<u>Weight</u>
22305	5 Gal.	Each	45 lbs.
22301	1 Gal.	Case of 4	40 lbs.